

## SPECIFICATIONS AND FIELDS OF EMPLOYMENT

Flexible wall coating, it allows you to obtain decorative finishes in relief of extraordinary beauty with extreme ease of implementation and with a pleasant tactile softness like "egg shell".

NAHIR allows the designer to pull out all his inspiration and his endless creativity and allows for customizable working. NAHIR is used as a basis (tinted white or colored) for shaping relief of any form and in the absence of absolute withdrawal up to 5 mm. Thick.

when completely dried it can be decorated with our VELATURA (properly pigmented) in the application process NAHIR enhances its characteristics:

- Excellent fluency and lightness in drawing
- high Open time (in order to reduce or cancel the problem of joints)
- Excellent power filler
- No withdrawal up to a thickness of 5 mm.

## COMPOSITION

Valuable resins in water emulsion, special extenders high resistance, titanium oxides and / or iron, additives. And free from harmful substances such as solvents and pigment-based or lead chromate.

## METHOD OF APPLICATION:

NAHIR is proposed with three decorative techniques of great aesthetic impact: NAHIR RIGATO, CRACKLE NAHIR', NAHIR BROCCATO.

## NAHIR RIGATO

This is an innovative solution furnishing of extraordinary beauty and ease of implementation that is suitable for use in both style ethnic (wengè effect or effect douglas), in a modern style (dark shades and stripes dyed light).

## Smooth well cohesive or plasterboard

Applying one coat of PRIMER S with roller or brush, minimum 12 hours after proceed with the drafting of NAHIR with a stainless steel trowel taking care to distribute a uniform layer of between 2 to 3 mm.

Immediately after with a special PETTINARTE finish NAHIR in a vertical or horizontal (depending on the desired effect), after drying (24h or better 48 h), apply VELATURA hue of choice with our SPUGNARTE following the direction of the lines.

## NAHIR BROCCATO

It also has a solution furnishing of great impact, ease of implementation, which is used in both modern in style.

## Smooth well cohesive or plasterboard

Applying one coat of PRIMER S with roller or brush, minimum 12 hours after proceed with the drafting of NAHIR with a stainless steel trowel taking care to distribute a uniform layer of between 2 to 3 mm.

Immediately after with a special PETTINARTE finish NAHIR in a vertical or horizontal (depending on the desired effect), after drying (24h or better 48 h), apply VELATURA hue of choice with our SPUGNARTE following the direction of the lines.

## NAHIR CRACKLE'

This is a very prestigious finish: particular and original if finished with VELATURA CLASSIC, also elegant and valuable if further complemented with VELATURA PERLATA

## Smooth well cohesive or plasterboard

Applying one coat of PRIMER S with roller or brush, minimum 12 hours after proceed with the drafting of NAHIR with a stainless steel trowel taking care to distribute a uniform layer of between 2 to 3 mm.

Immediately after with a special PETTINARTE finish NAHIR in a vertical or horizontal (depending on the desired effect), after drying (24h or better 48 h), apply VELATURA hue of choice with our SPUGNARTE following the direction of the lines.

### TECHNICAL DATA

SPECIFIC WIEGHT :	1,083 +/- 0,5% kg./Lt.
FILM ASPECT:	matt.
COLOURS:	white + colors from our color chart
VISCOSITY :	40000 cps +/- 5%
YIELD :	2 - 3 m <sup>2</sup> /Lt. per coat
DILUTION:	ready to use
PACKAGE:	buckets of Lt. 15 – 5 – 0,750
DRYING:	2 – 3 h to touch , 7 days to dry completely (temperature 20°C)
APPLICATION:	trowel or brush
PRESERVATION	36 months in the intact packages, away from temperature changes.

### ITEM OF SPECIFICATIONS

#### NAHIR RIGATO

Decoration of internal wall surfaces with shaped stripe effect on the type of RIGATO NAHIR , the consumption of about 2-3 m<sup>2</sup> / Lt. After applying a coat of micro granular fund rugged type D PRIMER ., and finished with VELATURA I.

The price includes the equipment and implementation, excluding the scaffolding m<sup>2</sup> €.....

#### NAHIR BROCCATO

Decoration of internal wall surfaces coated mural shaped brocade effect on the type of BROCCATO NAHIR , the consumption of about 2-3 m<sup>2</sup> / Lt. After applying a coat of micro granular fund rugged type D PRIMER ., and finished with VELATURA

The price includes the equipment and implementation, excluding the scaffolding m<sup>2</sup> €.....

#### NAHIR CRACKLE'

Decoration of internal wall surfaces coated mural shaped effect cracklè type NAHIR CRACKLE , the consumption of about 2-3 m<sup>2</sup> / Lt. After applying a coat of micro granular fund rugged type D PRIMER , a hand FISSATIVO REOSAN and a hand BASE CRACKLE ' , and finished VELATURA

The price includes the equipment and implementation, excluding the scaffolding m<sup>2</sup> €.....

NB The above-mentioned data are susceptible of variations. Atova Is not responsible for any negative result depending on the application of the product out of the company's control and on the agents unrelated to the product quality.